KRONOswiss®

THE ORIGINAL SWISS FLOOR

The world first laminate floor

KRONOswiss®

THE ORIGINAL SWISS FLOOR

The world first laminate floor

KRONOSWISS A

KRONOSWISS B

KRONOSWISS A

KRONOSWISS A



KRONOswiss®
THE ORIGINAL SWISS FLOOR
The world first laminate floor

Technical Data

Technical Specification

Test Standard	Test Institute	Test	Results
EN 13329	WKI	Resistance to impact test	Impact Test Category NK 23-31: IC1, NK 32: IC2, NK 33: IC3
EN 120	WKI	Externally controlled Formaldehyde Test	E1 HDF
EN 13329	WKI	Resistance to staining	Group 1-2: Level 5, Group 3: Level 4
EN 13329	WKI	Resistance to light	Blue wool scale: not worse than 6, Grey Matter: No worse than 4
EN 13329	WKI	Resistance to burning cigarette	Level 4
EN ISO 9239-1 EN ISO 11925-2 EN 13501-1	MPA	Reaction to Fire	Flame-retardant, Building Class Cfl-s1
EN 13329	WKI	Effect of a moving Furniture coaster	No visible reaction to coaster type 0
EN 13329	WKI	Wheelchair Test	No visible changes or damage, as defined in EN 425
DIN 52612	eph	Thermal Conductivity	$\lambda_{10,fr}$ = 0.17 W/m·K, Suitable for underfloor heating (medium: water)
		Disposal	Disposal as per household waste

Further information can be found at: www.kronospan.com

Utilisation Categories

	little utilisation	medium utilisation	intensive utilisation
living	 **AC 1 / Kl. 21** bed-, guestrooms	 **AC 2 / Kl. 22** living-, dining rooms	 **AC 3 / Kl. 23** kitchen, entrance halls
commercial	 **AC 3 / Kl. 31** hotel rooms, small offices	 **AC 4 / Kl. 32** offices, boutiques	 **AC 5 / Kl. 33** stores, corridors

Symbols

suitable for Bedrooms

suitable for Living rooms

suitable for kitchens

suitable for dining areas

suitable for office space

suitable for hotels

suitable for shops

Kronoswiss® Limited Residential Warranty
Kronoswiss® offers some of the best consumer warranties in the industry. For the complete warranty details and terms please visit www.kronoswiss.com